



MATERIAL DATASHEET

(Revision 05-11-2021)

GENERAL PROPERTIES	
Compound name:	NDS-100
Compound description:	PTFE Virgin
Color:	White
Operating temperature range:	-200°C to +260°C
Approvals/certifications:	NSF/ANSI 61 certified, FDA compliant

MATERIAL PROPERTIES			
Property (conditions)	Specified	Unit	Standard
Hardness (at 23°C)	55	Shore D	ISO 868
Specific gravity (at 23°C)	2,16	g/cm ³	ISO 1183
Ball indentation hardness (at 23°C H132/60)	28	MPa	ISO 2039-1
Water absorption (24 hours)	<0.01	%	ASTM D570
Mechanical			
Tensile strength (test speed 50mm/min)	22	MPa	ISO 527
Elongation at break (test speed 50mm/min)	250	%	ISO 527
Tensile modulus (test speed 50mm/min)	550	MPa	ISO 527
Compressive strength (1% deformation)	4.5	N/mm ²	ASTM D695
Deformation under load (at 23°C , 24h@13,7 N/mm ²)	15	%	ASTM D621
Permanent deformation (as above, after 24h of rest)	8	%	ASTM D621
Izod notched impact strength (23°C)	155	J/m	ASTM D256
Thermal			
Coefficient of thermal linear expansion (25°C/95°C)	12	10 ⁻⁵ /°C	ASTM D696
Service temperature	-200°C to +260	°C	-
Melting temperature (10°C/min)	327	°C	ISO 11357
Flame rating (3-6mm)	V-0	Class	UL 94
Heat deflection temperature (1.8 MPa)	50	°C	ISO 75



Electrical			
Dielectric strength (0.5mm thickness)	60	Kv/mm	IEC 60243-1
Dielectric constant (60 to 2 x 109 Hz)	2.1	-	ASTM D150
Dissipator factor (60 to 2 x 109 Hz)	0.0001	-	ASTM D150
Volume resistivity (23°C)	10 ¹⁸	Ω*cm	IEC 60093
Surface resistivity (23°C)	10 ¹⁷	Ω	IEC 60093
Tribological			
Coefficient of static friction	0.04-0.08	-	ASTM D3702
Coefficient of dynamic friction	0.05-0.10	-	ASTM D3702
Miscellaneous			
Weathering resistance	Excellent	-	Weather-O-Meter
Chemical resistance	Excellent	-	ASTM D543

Disclaimer

This information is to the best of our knowledge accurate to the date indicated. However, NewDealSeals make no warranty, expressed or implied that parts manufactured from this material will perform satisfactorily in the customer's application. It is the customer's responsibility to evaluate parts prior to use, especially in applications where their failure may result in injury and/or damage. It should also be noted that all elastomeric parts have a finite life, therefore a regular program of inspection and replacement is strongly recommended. TGA, infrared and other types of analysis must be agreed, fixed and approved by both parties with specifications and tolerances; on the contrary results can neither confirmed nor guaranteed. Nothing herein shall be construed as a recommendation to infringe any existing patent or violate any applicable law. The distribution of this document is not monitored. This data sheet is not subject to an automatic update.